

Substrate	Primer	Required for adhesion	Purpose	Coverage Rate
Aged Asphalt	P-160	X	Prevents yellowing due to bleed through.	1 gallon per 100sf
Concrete	P-140	✓	*Only use if concrete is under 1 year old.	1 gallon per 150-200sf
EPDM	P-120	✓	Cleans off black film from EPDM. *Only needed if you have poor adhesion.	1 gallon per 500sf
EPDM	P-110	X	Prevents yellowing due to bleed through.	1 gallon per 200sf
Granulated Cap Sheet	P-160	X	Prevents yellowing due to bleed through.	1 gallon per 100sf
Gravel BUR	P-160	X	Prevents yellowing due to bleed through.	1 gallon per 100sf
Hypalon	P-151 P-152	✓	Removes oily firm present on many single-ply roofs. Most commonly required on roofs less than 5 years old.	.25- .33 gallon per 100sf. See TDS
Metal	P-130	X	Virtually stops current rust growth and prevents future rust growth.	1 gallon per 200sf
Modified Bitumen	P-160	X	Prevents yellowing due to bleed through.	1 gallon per 100sf
PVC	P-151 P-152	✓	Removes oily firm present on many single-ply roofs. Most commonly required on roofs less than 5 years old.	.25- .33 gallon per 100sf. See TDS
Smooth BUR	P-160	X	Prevents yellowing due to bleed through.	1 gallon per 100sf
SPF	P-100	X	Protects foam from oxidizing under UV rays	1 gallon per 200sf
TPO	P-151 P-152	✓	Removes oily firm present on many single-ply roofs. Most commonly required on roofs less than 5 years old.	.25- .33 gallon per 100sf. See TDS