



PRO prime

Technical Product Data

P-110 EPDM Bleed-Block

BASIC USES & DESCRIPTION:

P-110 is a plasticizer free, single component, water-based, acrylic primer designed to prime properly cleaned EPDM surfaces. P-110 is formulated to provide excellent adhesion for silicone over EPDM surfaces, while also blocking the discoloration caused by chemicals bleeding out of the EPDM membrane.

LIMITATIONS & PRECAUTIONS:

This product cures only by water evaporation. P-110 should not be applied when the ambient temperature is below 50°F, or if there is a possibility the temperature could fall below 32°F within 24 hours. Application is not recommended if rain or dew is expected before product dries.

APPLICATION:

P-110 is intended to be spray-applied. It can also be applied with a brush or roller. P-110 should be applied at a rate of 1gallon per 200 square feet. Surface should be clean and dry prior to application. P-110 should not be applied on roofs with slopes less than 1/8" in

12". **SPRAY:** Contact Progressive Materials for specific pump, hose, and spray gun requirements. **ROLLER:** 1¼" nap roller.

BRUSH: Synthetic filament.

STORAGE AND SHELF LIFE:

P-110 is a water based primer and is not freeze-thaw stable. P-110 should be stored between 40°F and 70°F. Shelf life in unopened containers is 24 months from the manufacture date.

PACKAGING SIZES:

P-110 EPDM Bleed-Block Primer is available in 5 gallon and 55 gallon containers.

TYPICAL PROPERTIES

As Supplied:			
Appearance:	Gray	Clean Up	Water
Total Solids (volume):	50% +/- 2%	Shelf Life	24 Months
Weight Per Gallon	12.1 lbs. per gallon +/- 0.2	Viscosity	110 +/-10KU
VOC:	< 50 grams/liter		

The information reported herein are based upon information reasonably available to Progressive Materials, LLC at the time publication, and are presented in good faith but are not to be construed as warranties or guarantees, expressed or implied.

Contact Progressive Materials for more detailed specifications on our roofing systems and to find a certified contractor near you.



Revision Date: November 7, 2016